


检验检测报告



No: 240061198

防伪查询网址: www.gttctech.com

防伪码: YJHL-4651-04

共3页 第1页

扫码下载报告



委托单位	上海支米空气净化科技有限公司 地址: 上海市松江区泗泾镇米易路166号1幢201室				
客户认定信息	复合染色布料 20cm×200cm 颜色: 蓝白 材质: 涤氨覆膜 单位面积质量: 230g/cm ² 生产单位: 上海支米空气净化科技有限公司				
检验性质	委托检测	样品受理/测试开始日期	2024-03-18	报告签发日期	2024-03-21
判定依据	GB 31701-2015 《婴幼儿及儿童纺织产品安全技术规范》				
综合检验结论	---				
检验检测结果	检验检测项目	判定依据		判定	
	耐汗渍色牢度	GB 31701-2015		符合	
	耐水色牢度	GB 31701-2015		符合	
	耐摩擦色牢度	GB 31701-2015		符合	
	耐唾液色牢度	GB 31701-2015		符合	
备注	本报告中检验检测项目均在相应标准规定的环境条件下进行(有注明的除外)。复印件、副本未重新加盖报告书确认章无效。本报告检验检测地址为广州市番禺区珠江路1号。				

签发: 陈少娟 工程师

陈少娟



样品图片

No:240061198

共3页 第2页



检验检测报告附页

No: 240061198

共3页 第3页

检验检测项目 (计量单位) [样品识别]	测试方法	标准值及允差	检验检测结果	判定	备注
●耐汗渍色牢度 (级)	GB/T 3922-2013	变色 $\geq 3-4$ 沾色 $\geq 3-4$	变色 酸 4 碱 4 沾色 -醋纤 4-5 4-5 -棉 4-5 4-5 -锦纶 4-5 4-5 -涤纶 4-5 4-5 -腈纶 4-5 4-5 -羊毛 4-5 4-5	符合	---
●耐水色牢度(级)	GB/T 5713-2013	变色 $\geq 3-4$ 沾色 $\geq 3-4$	变色 4 沾色 -醋纤 4-5 -棉 4-5 -锦纶 4-5 -涤纶 4-5 -腈纶 4-5 -羊毛 4-5	符合	---
●耐摩擦色牢度 (级)	GB/T 3920-2008	干摩 ≥ 4 湿摩 ≥ 3	干摩 4-5 湿摩 4-5	符合	---
●耐唾液色牢度 (级)	GB/T 18886-2019	变色 ≥ 4 沾色 ≥ 4	变色 4 沾色 -醋纤 4-5 -棉 4-5 -锦纶 4-5 -涤纶 4-5 -腈纶 4-5 -羊毛 4-5	符合	---
备注	(本栏空白)				



本报告结论

注意事项

1. 报告书未加盖检测单位检验检测专用章无效。
2. 复印件未加盖检测单位报告确认章无效。
3. 对委托送检结果有异议的，应于报告书送达之日起十五日内提出。
4. 检测结果仅对所检样品有效。
5. 未取得资质认定的项目，仅作为科研、教学或内部质量控制之用。
6. 报告书涂改无效。
7. 客户提供的信息（包括样品信息），本公司/中心不对其真实性负责。
8. 未经本公司/中心书面批准不得部分复制本报告，全部复制除外。

Note

1. The report is invalid without authorized stamp.
2. Copies of this report are invalid without authorized stamp.
3. Any dispute should be raised within 15 days after receiving the report.
4. The result is only valid for the tested sample.
5. The results of unapproved items are for reference only.
6. This report is invalid if altered.
7. Our company does not accept any responsibility for the authenticity of the information supplied by customers (including sample information).
8. The report shall not be duplicated separately or partly, without prior written permission approved by GTTC, except duplicated in full version.